

OK 46.00



OK 46.00 is the best, all-round, rutile electrode and it is relatively insensitive to rust or other surface impurities. It deposits smooth weld beads in all positions, including vertical down, and the slag is easy to remove. OK 46.00 is very easy to strike and restrike, making it ideal for short welds, root runs and tacking.

Clasificaciones	SFA/AWS A5.1 : E6013 EN ISO 2560-A : E 38 0 RC 11 GOST 9467-75 : E46 GOST R ISO 2560-A : E 38 0 RC 11
Aprobaciones	ABS 2 BV 2 CE EN 13479 DB 10.039.05 DNV 2 GL 2 LR 2 RS 2 VdTUV 00623 BKI 2 ClassNK KMW2 NAKS/HAKC 2.5 3.0 4.0 5.0 mm NAKS/HAKC 3.0-4.0 mm NAKS/HAKC 3.2-4.0 mm RRR 2

Las aprobaciones dependen de la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

Corriente de soldadura	AC, DC+-
Tipo de aleación	Carbon Manganese
Tipo de recubrimiento	Rutile-cellulosic covering

Propiedades tensoras típicas

Condición	Límite de elasticidad	Resistencia a la tracción	Alargamiento
ISO			
As Welded	400 MPa	510 MPa	28 %

Propiedades de Ensayo de impacto Charpy

Condición	Temperatura de ensayo	Valor de impacto
ISO		
As Welded	0 °C	70 J

à% Análisis metal depositado (valores típicos)

C	Mn	Si
0.08	0.42	0.30

Datos aportación

Diámetro	Amperios	Voltios	Número de electrodos/kg de metal de soldadura	Tiempo de fusión por electrodo al 90 % I máx.	Rendimiento %	Deposition Rate @ 90% I max
1.6 x 300.0 mm	30-60 A	26 V	263	36 sec	63 %	0.38 kg/h
2.0 x 300.0 mm	50-70 A	25 V	172	38 sec	60 %	0.55 kg/h
2.5 x 350.0 mm	60-100 A	22 V	86	50 sec	65 %	0.8 kg/h
3.0 x 350.0 mm	70-140 A	32 V	77	46 sec	51 %	1.0 kg/h
3.2 x 350.0 mm	80-150 A	22 V	53	57 sec	65 %	1.3 kg/h
3.2 x 450.0 mm	80-150 A	22 V	43	63 sec	64 %	1.33 kg/h
4.0 x 400.0 mm	100-200 A	26 V	33	64 sec	60 %	1.69 kg/h
4.0 x 450.0 mm	100-200 A	23 V	33	76 sec	58 %	1.94 kg/h
5.0 x 350.0 mm	150-290 A	24 V	24	87 sec	60 %	2.3 kg/h
5.0 x 400.0 mm	150-290 A	30 V	22	71 sec	56 %	2.2 kg/h
5.0 x 450.0 mm	150-290 A	24 V	31	114 sec	60 %	2.3 kg/h